

DATA SHEET

2002W

Properties	Test Method	Value	
Grab Tensile Strength	ASTM D4632	200 lbs	890 N
Grab Tensile Elongation	ASTM D4632	15%	
Puncture Resistance	ASTM D4833	95 lbs	422 N
Trapezoid Tear	ASTM D4533	75 lbs	330 N
Mullen Burst	ASTM D3786	460 psi	3170 kPa
Flow Rate	ASTM D4491	4 gpm/ft ²	160 l/min/m ²
Permittivity	ASTM D4491	0,05 sec ⁻¹	
Apparent Opening Size (AOS)	ASTM D4491	40 US Sieve	0,425 mm
UV Resistance (500 hours)	ASTM D4355	70%	
Roll Width		3,81 meters	
Roll Length		131 meters	

Type of Fiber : Polypropylene
 Type of Construction : Woven

The enclosed information is provided by Soleno Textiles Inc. at no cost and without liability on the part of the company. The individual using this information assumes full responsibility for its application, and undertakes to contact Soleno Textiles Inc. to ensure that this technical sheet is the most recent version available. The values are calculate by the MARV system as specify by ASTM D-4439. Roll sizes can vary by 0.5% from the standard. Soleno Textiles Inc. offers no guarantee as to the use, installation and/or suitability of the geotextiles described in this document. Since conditions surrounding the use and handling of our products can vary and are beyond the control of Soleno Textiles Inc., the latter can, in no way, be held responsible for the performance of the products, nor consequences arising from their improper installation or use. Soleno Textiles Inc. must be informed of any product defect or deficiency noted prior to installation. The liability of Soleno Textiles Inc. will be limited to the replacement of the deficient or defective product to the exclusion of any legal or contractuel warranty.