

TECHNICAL CHART

TXC-10

Properties	Test Method	Value
Grab Tensile Strength	CAN-148.1 - no 7.3	95 N
Grab Tensile Elongation	CAN-148.1 - no 7.3	65 - 105%
Permeability	CAN-148.1 - no 4	1.5×10^{-1} cm/sec
Permittivity	CAN-148.1 - no 4	2.0 s^{-1}
Filtration Opening Size	CAN-148.1 - no 10	90 - 150 microns
Watering (Moistening)	CAN-4.2 - no 26.3	less than 1 cm

Type of Fiber : 100 % polyester (white)

Type of Construction : Needle Punched Non Woven

The enclosed information is provided by Soleno Textiles Inc. at no cost and without liability on the part of the company. The individual using this information assumes full responsibility for its application, and undertakes to contact Soleno Textiles Inc. to ensure that this technical sheet is the most recent version available.

The values are calculate by the MARV system as specify by ASTM D-4439. Roll sizes can vary by 0.5% from the standard. Soleno Textiles Inc. offers no guarantee as to the use, installation and/or suitability of the geotextiles described in this document. Since conditions surrounding the use and handling of our products can vary and are beyond the control of Soleno Textiles Inc., the latter can, in no way, be held responsible for the performance of the products, nor consequences arising from their improper installation or use. Soleno Textiles Inc. must be informed of any product defect or deficiency noted prior to installation.

The liability of Soleno Textiles Inc. will be limited to the replacement of the deficient or defective product to the exclusion of any legal or contractuel warranty.